




SiSiB[®] PC7940 SILANE

- 1 -

CHEMICAL NAME

Tetraacetoxysilane [Developmental]

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PC7940 is a clear to yellowish liquid with acrid odor of acetic acid (vinegar). It hydrolyzes in the presence of moisture (acetic acid is released) to form silanols, which can react with themselves to produce siloxanes or bind to inorganic substrates.

TYPICAL PHYSICAL PROPERTIES

CAS No.	562-90-3
EINECS No.	209-239-7
Formula	C ₈ H ₁₂ O ₈ Si
Molecular Weight	264.26
Boiling Point	148°C [760mmHg]
Melting Point:	111-115°C
Flash Point:	150°C
Color and Appearance	Off-white crystalline solid
Density _{25/25°C}	1.18
Active Content	Min.95.0%

APPLICATIONS

Acetoxy silanes are more reactive than alkoxy silanes. Acetoxy silanes are frequently used as one-component mixtures to make RTV-1 silicone sealants. These mixtures have an excess of multi-functional acetoxy silane added to silanol-terminated PDMS, which results in a PDMS chain with acetoxy groups at the ends. When this compound is exposed to moisture some acetoxy groups are hydrolyzed and self-condense or react

Power Chemical
ISO9001 ISO14001 certified

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] PC7940 SILANE

- 2 -

with other acetoxo and rapid crosslinking takes place. Acetic acid formation is one of the driving forces of this reaction.

PACKING AND STORAGE

Customized product packing is 100ml, 250ml, 500ml, 1L and 5L bottle. Industrialized product packing is 210L steel drum or 1000L IBC tote.

In the unopened original container SiSiB[®] PC7940 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: silanes@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia