



INTRODUCTION

SiSiB® HR2560 is the high rebound resilience heat cured silicone elastomers for molding.

KEY FEATURES

High rebound resilience

Excellent process ability.

Well balanced physical properties

50, 60, 70 durometer grades available

ROHS test passed

TYPICAL PHYSICAL PROPERTIES

Product	SiSiB® HR2560 HCE
Appearance	Transparent
Curing Agent	C-15
Curing Agent Content	2.0%
Curing Condition	170°C × 10min
Hardness (Shore A)	60+/-2
Tensile Strength (MPa)	Min. 8.5
Elongation (%)	Min. 280
Tensile Set (%)	Max. 8.0
Tear Strength (KN/m)	Min. 24.0

APPLICATIONS

Long life Keypad

Gasket/Roller

Parts

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB® is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia



SiSiB[®] HR2560 HCE

- 2 -

PACKING AND STORAGE

SiSiB[®] HR2560 is supplied in 20Kg box, with plastic bag inside.

Store in a cool and dry place out of direct sunlight.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

Power Chemical
ISO9001 ISO14001 certificated

Copyright© 2008 Power Chemical Corporation Ltd.
SiSiB[®] is a registered trademark of PCC. For more knowledge regarding organosilanes, you may visit www.SiSiB.com or www.PCC.asia